Attorney Dooket No. 2003-0250 / 24061.144 Customer No. 42717

Amendments To The Claims

Please cancel Claims 27-32 without prejudice. The following list of the claims replaces all prior versions and lists of the claims in this application.

(Original) A method for forming an opening in a semiconductor device comprising:
 forming an anti-reflective coating (ARC) layer above an insulation layer of a substrate;
 forming a patterned photoresist layer including at least one opening therein above the
 ARC layer;

etching the ARC layer and the insulation layer in a process comprising:

introducing a first gas including fluorocarbon gas for etching and polymer formation;

introducing a second gas containing oxygen for polymer formation control; and

partial etching the ARC layer defined by the at least one opening and subsequently forming a polymer layer on the inside of the at least one opening.

2. (Original) The method of claim 1, further comprising:

repeating the step of partial etching and polymer formation to form the at least one opening in the ARC layer; and

continuing the step of partial etching and polymer formation to form the at least one opening in the insulation layer.

- 3. (Original) The method of claim 1, wherein the opening includes a contact.
- 4. (Original) The method of claim 1, further comprising forming an etch stop layer above the substrate prior to the step of forming the insulation layer.

Attorney Docket No. 2003-0250 / 24061.144 Customer No. 42717

5. (Original) The method of claim 4, further comprising: removing the photoresist layer and the ARC layer; and

continuing the step of partial etching and polymer formation to form the at least one opening in the etch stop layer, such that a conductive layer is subsequently formed in the at least one opening in the insulation layer and the etch stop layer to electrically contact an active region of a transistor.

- 6. (Original) The method of claim 1, wherein the insulation layer includes an interlayer dielectric (ILD).
- 7. (Original) The method of claim 1, wherein the fluorocarbon gas comprises CxFy, where x ranges from 0 to 9 and y ranges from 0 to 9.
- 8. (Original) The method of claim 1, wherein the fluorocarbon gas comprises CxHyFz, where x ranges from 0 to 9, y ranges from 0 to 9, and z ranges from 0 to 9.
- 9. (Original) The method of claim 1, wherein the second gas is selected from the group consisting of O2, CO, CO2, NO, N2 and NO2.
- 10. (Original) The method of claim 1, further comprising: introducing a third gas for diluent and ion density control selected from the group consisting of Ar, He, Kr, and Xe.
- 11. (Original) The method of claim 1, wherein the photoresist layer and the ARC layer are subsequently removed such that a conductive layer is subsequently formed in the at least one opening in the insulation layer to electrically contact an active region of a transistor.
 - 12. (Original) The method of claim 1, wherein the opening includes a via.

Attorney Docket No. 2003-0250 / 24061.144 Customer No. 42717

- 13. (Original) The method of claim 1, wherein the insulation layer includes an intermetal dielectric (IMD).
- 14. (Original) The method of claim 1, wherein the photoresist layer and the ARC layer are subsequently removed such that a conductive layer is subsequently formed in the at least one opening in the insulation layer to electrically contact a metal layer formed above the substrate.
- 15. (Original) A method for forming an opening in a semiconductor device comprising: forming a first anti-reflective coating (ARC) layer above an insulation layer of a substrate;

forming a first photoresist layer having a first patterned opening therein; etching the first ARC layer and the insulation layer in a process comprising:

introducing a first gas including fluorocarbon gas for etching and polymer formation;

introducing a second gas containing oxygen for polymer formation control;

partial etching the first ARC layer defined by the first patterned opening and subsequently forming a polymer layer on the inside of the first patterned opening;

repeating the step of partial etching and polymer formation to form the first patterned opening in the first ARC layer;

continuing the step of partial etching and polymer formation to form the first patterned opening in the insulation layer;

removing the first photoresist layer and the first ARC layer;
forming a second ARC layer above the insulation layer;
forming a second photoresist layer having a second patterned opening therein;
etching the second ARC layer and the insulation layer in a process comprising:
introducing the first and second gas;

Attorney Docket No. 2003-0250 / 24061.144 Customer No. 42717

partial etching the second ARC layer defined by the second patterned opening and subsequently forming a polymer layer on the inside of the second patterned opening;

repeating the step of partial etching and polymer formation to form the second patterned opening in the second ARC layer; and

continuing the step of partial etching and polymer formation to form the second patterned opening in the insulation layer.

- 16. (Original) The method of claim 15, wherein the opening includes a dual damascene opening.
 - 17. (Original) The method of claim 15, wherein the first patterned opening is a via.
- 18. (Original) The method of claim 15, wherein the second patterned opening is a trench.
- 19. (Original) The method of claim 15, further comprising forming an etch stop layer prior to the step of forming the insulation layer.
- 20. (Original) The method of claim 19, further comprising:
 removing the first photoresist layer and the first ARC layer; and
 continuing the step of partial etching and polymer formation to form the first patterned
 opening in the etch stop layer, such that a conductive layer is subsequently formed in the first
 and second patterned openings in the insulation layer to electrically contact a metal layer formed
 above the substrate.
- 21. (Original) The method of claim 15, wherein the insulation layer includes an intermetal dielectric (IMD).

Attorney Docket No. 2003-0250 / 24061.144 Customer No. 42717

- 22. (Original) The method of claim 15, wherein the fluorocarbon gas comprises CxFy, where x ranges from 0 to 9 and y ranges from 0 to 9.
- 23. (Original) The method of claim 15, wherein the fluorocarbon gas comprises CxHyFz, where x ranges from 0 to 9, y ranges from 0 to 9, and z ranges from 0 to 9.
- 24. (Original) The method of claim 15, wherein the second gas is selected from the group consisting of O2, CO, CO2, NO, N2 and NO2.
- 25. (Original) The method of claim 21, further comprising: introducing a third gas for diluent and ion density control selected from the group consisting of Ar, He, Kr, and Xe.
- 26. (Original) The method of claim 15, wherein the second photoresist layer and the second ARC layer are subsequently removed such that a conductive layer is subsequently formed in the first and second patterned openings in the insulation layer to electrically contact a metal layer formed above the substrate.

Claims 27-32 (Canceled).